

# R4 chorus GLOSS

## CARTE PER STAMPE DI PREGIO - FINE PAPERS

### CARTE PATINATE SENZA LEGNO - COATED WOODFREE PAPER (CWF)



<b>Grammatura Substance</b>	<b>ISO 536</b>	<b>g/m<sup>2</sup></b>	<b>90</b>	<b>100</b>	<b>115</b>	<b>130</b>	<b>135</b>	<b>150</b>	<b>170</b>	<b>200</b>	<b>250</b>	<b>300</b>	<b>350</b>
Spessore <i>Caliper</i>	ISO 534	$\mu m$	70	76	84	95	97	108	122	146	188	235	275
Volume specifico <i>Bulk</i>	ISO 534	$cm^3/g$	0.78	0.76	0.73	0.73	0.72	0.72	0.72	0.73	0.75	0.78	0.78
Lucido Gardner <i>Gloss Gardner</i>	ISO 8254-1	%	71	73	77	78	78	78	78	78	78	75	75
Grado di bianco CIE <i>Whiteness CIE</i>	ISO 11475	%	119	119	119	119	119	119	119	119	119	119	119
Bianco ISO <i>Brightness ISO</i>	ISO 2470 (D65)	%	94.5	94.5	94.5	95	95	95	95	95	95	95	95
Opacità ISO <i>Opacity ISO</i>	ISO 2471	%	91	93.5	95	96	96.5	97	97 min	98 min	98 min	98 min	98 min

Finitura *Finishing*

Gloss

Tipo di stampa *Printing methods*

Sheet-fed offset

Applicazioni *End uses*

Brochure, Cataloghi, Copertine di libri e di riviste, Direct Mailing, Inserti, Libri, Libri d'arte e di lusso, Periodici, Report commerciali e finanziari, Riviste di pregio, Stampe commerciali  
*Brochures, Catalogues, Books and publishing covers, Direct Mailing, Inserts, Books, Art and luxury books, Magazines, Business and financial reports, Luxury magazines, Commercial printing*

I valori relativi ai singoli prodotti sono forniti a titolo esemplificativo e possono essere soggetti a modifiche senza preavviso. Ogni valore è soggetto a determinate tolleranze.  
*Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.*

**BURGO**  
GROUP